

6-OUNCE NONWOVEN GEOTEXTILE TUBE

6" staking flap and no lifting straps or ports
Size: 11.5' circumference by 360' length (5.75' lay flat)

Nonwoven geotextile tube is a needle-punched nonwoven geotextile manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position.

Nonwoven geotextile tube resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV English	MARV Metric
Tensile Strength (Grab)	ASTM D-4632	160 x 160 lbs	711 x 711 N
Elongation	ASTM D-4632	50%	50%
CBR Puncture	ASTM D-6241	410 lbs	1825 N
Trapezoidal Tear	ASTM D-4533	60 x 60 lbs	267 x 267 N
UV Resistance (500 hrs)	ASTM D-4355	70%	70%
Apparent Opening Size (AOS)*	ASTM D-4751	70 US Std. Sieve	0.212 mm
Permittivity	ASTM D-4491	1.4 sec ⁻¹	1.4 sec ⁻¹
Water Flow Rate	ASTM D-4491	105 gpm/ft ²	4276 lpm/m ²

*Maximum Average Roll Valve

Notes:

- Mullen Burst ASTM D-3786 has been removed. It is not recognized by ASTM D-35 on Geosynthetics.
- Puncture ASTM D-4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D-6241