

8-OUNCE NONWOVEN GEOTEXTILE TUBE

6" staking flap and no lifting straps or ports
Size: 14' circumference by 300' length (7' lay flat)

Nonwoven geotextile tube is a needle-punched nonwoven geotextile manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position.

Nonwoven geotextile tube resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV English	MARV Metric
Tensile Strength (Grab)	ASTM D-4632	205 x 205 lbs	912 x 912 N
Elongation	ASTM D-4632	50%	50%
CBR Puncture	ASTM D-6241	525 lbs	2336 N
Trapezoidal Tear	ASTM D-4533	80 x 80 lbs	356 x 356 N
UV Resistance (500 hrs)	ASTM D-4355	70%	70%
Apparent Opening Size (AOS)*	ASTM D-4751	80 US Std. Sieve	0.18 mm
Permittivity	ASTM D-4491	1.4 sec ⁻¹	1.4 sec ⁻¹
Water Flow Rate	ASTM D-4491	90 gpm/ft ²	3667 lpm/m ²

*Maximum Average Roll Valve

Notes:

- Mullen Burst ASTM D-3786 has been removed. It is not recognized by ASTM D-35 on Geosynthetics.
- Puncture ASTM D-4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D-6241