

Specification Sheet **EroNet™ P300® LW** Permanent Erosion Control Blanket


DESCRIPTION

The permanent erosion control blanket shall be a machine-produced mat of 100% UV stable polypropylene fiber. The matting shall be of consistent thickness with the synthetic fibers evenly distributed over the entire area of the mat. The matting shall be covered on the top and bottom side with a UV-stabilized polypropylene net with a 0.63 x 0.63 inch (1.57 x 1.57 cm) mesh size. The blanket shall be sewn together on 1.50 inch (3.81 cm) centers with non-degradable thread. All mats shall be manufactured with a colored thread stitched along both outer edges as an overlap guide for adjacent mats.

The P300LW shall meet Type 5A, 5B, specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.18

Material Content			
Matrix	100% UV-stablized polypropylene Fiber Weave	0.5 lbs/sq yd (0.27 kg/sm)	
Netting	Top and bottom net, UV-stabilized polypropylene	3 lbs/1000 sq ft (14.7 g/sm)	
Thread	Polypropylene, UV stable		
Standard Roll Sizes			
Width	6.67 ft (2.03 m)	8 ft (2.44 m)	
Length	108 ft (32.92 m)	112 ft (35.14 m)	
Weight ± 10%	45 lbs (20.4 kg)	56.25 lbs (25.5 kg)	
Area	80 sq yd (66.9 sm)	100 sq yd (83.61 sm)	

Slope Design Data: C Factors				
Slope Gradients (S)				
Slope Length (L)	≤ 3:1	3:1 - 2.1	≥ 2:1	
≤ 20 ft (6 m)	0.001	0.029	0.082	
20-50 ft	0.036	0.060	0.086	
≥ 50 ft (15.2 m)	0.070	0.090	0.110	



Index Property	Test Method	Typical
Thickness	ASTM D6525	0.30 in. (7.68 mm)
Density	ASTM D792	0.916 g/cm ³
Mass/Unit Area	ASTM 6566	8.92 oz/sy (300 g/m2)
UV Stability	ASTM D4355/ 1000 hr	90%
Light Penetration	ASTM D6567	27.6%
Tensile Strength - MD	ASTM D6818	430 lbs/ft (6.38 kN/m)
Elongation - MD	ASTM D6818	37%
Tensile Strength - TD	ASTM D6818	150 lbs/ft (2.22 kN/m)
Elongation - TD	ASTM D6818	28%
Biomass Improvement	ASTM D7322	471%

Design Permissible Shear Stress			
	Short Duration	Long Duration	
Phase 1: Unvegetated	2.0 psf (96 Pa)	2.0 psf (96 Pa)	
Phase 2: Partially Veg.	6.0 psf (287 Pa)	4.0 psf (191 Pa)	
Phase 3: Fully Veg.	8.0 psf (384 Pa)	8.0 psf (384 Pa)	

Roughness Coefficients – Unveg.			
Flow Depth	Manning's n		
≤ 0.50 ft (0.15 m)	0.030		
0.50 – 2.0 ft	0.030-0.018		
≥ 2.0 ft (0.60 m)	0.018		

©2019. North American Green is a registered trademark from Western Green. Certain

U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent

applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and

its manner of use, is the sole responsibility of the user. Printed in the U.S.A.

products and/or applications described or illustrated herein are protected under one or more



Western Green 4609 E. Boonville-New Harmony Rd. Evansville, IN 47725

nagreen.com 800-772-2040